
# **WEDOLIT AS 2241**

High-Protection-DW-Fluid 40°C flash point

(aromatic content ≤ 2%)





## **Physical Properties Typical Data**

| Parameter               | Typical results        | Tested according to   |
|-------------------------|------------------------|-----------------------|
| Appearance:             | Medium-brown, clear    | Visual                |
| Density at 15°C:        | 0.81 g/cm <sup>3</sup> | ASTM D 7042           |
| Viscosity at 20°C:      | 2.2 mm <sup>2</sup> /s | ASTM D 7042           |
| Flash point:            | > 45 °C                | DIN EN ISO 2719       |
| Film weight:            | 1.3 g/m <sup>2</sup>   | Dipping procedure     |
| Film type:              | Oily                   | Haptical              |
| Dewatering effect:      | ≤ 30 s                 | Internal test method  |
| Water separation:       | 4 min                  | Internal test method  |
| Humidity test:          | 120 cycles             | DIN EN ISO 6270-2 AHT |
| Salt spray performance: | 48 h                   | DIN EN ISO 9227 NSS   |

### **Application Guidelines**

Storage must be frost-free between 5 - 35°C.

The minimum durability is 12 months in an original sealed package.

#### **Additional Information**

The information herein is given in good faith and believed current as of the date of publication and should apply to the current formula version. Because conditions of use are beyond our control, no guarantee, representation or warranty expressed or implied is made. Consult Master Fluid Solutions for further information. For the most recent version of this document, please go to this URL: https://2trim.us/diw/?plr=AS-2241\*en\*eu

WEDOLIT AS 2241 ©2020-2024 Master Fluid Solutions™ | 2024-04-28



#### **Choose WEDOLIT AS 2241:**

- · Ideal for overseas transport
- Suitable for VCI-foils: The full corrosion protection is only given in the solvent-free film, therefore a short storage time until the solvent evaporates must be observed especially before packing in boxes with foils
- Stable against acidic and alkaline contamination
- Good material compatibility
- Water displacing with very good wetting behaviour
- Easily removable with organic solvents (cold cleaners) or watermiscible alkaline industrial cleaners
- Additive loss due to water contact: Extremely low

#### **Health and Safety**

For further information, see the most recent SDS which is available directly from Master Fluid Solutions.

Hasselsstraße 6-14 Düsseldorf, 40597 Germany +49 211 41 72 82 00

info-eu@masterfluids.com

masterfluids.com/eu/en/

