



# WEDOLiT CW 8906

*Water-miscible, ester-based coolant*



WEDOLiT CW 8906 is suitable for grinding as well as light to heavy cutting operations of steel, stainless steel, aluminium and titanium.



## Physical Properties Typical Data

### Concentrate

| Colour | Mineral oil content | Viscosity at 20°C: ASTM D 7042 | Density at 20°C: ASTM D 7042 | Copper corrosion: DIN 51759-1 |
|--------|---------------------|--------------------------------|------------------------------|-------------------------------|
| Brown  | Free                | 78.0 mm <sup>2</sup> /s        | 0.97                         | Not determined*               |

### 5% Solution

| Colour | pH-value (tap water) | Corrosion protection DIN 51360-2 | Refractometer factor (brix) | Conductivity (Deionised water) |
|--------|----------------------|----------------------------------|-----------------------------|--------------------------------|
| Beige  | 9.2                  | 4 % grade 0                      | 1.2                         | 880 µS/cm                      |

| Mineral oil | EP-additives | Chlorine | Boron | Amines | FAD |
|-------------|--------------|----------|-------|--------|-----|
| -           | +            | -        | -     | +      | -   |

\*Discolourations of non-ferrous metals should be examined in preliminary tests

## Application Guidelines

The preparation of the emulsion is carried out by slowly adding the concentrate into water (drinking water quality) under thorough stirring. A more homogenous product is achieved by the use of automatic mixing systems.

Storage must be frost-free between 5 - 40°C.

The minimum durability is 12 months in an original sealed package.

## Additional Information

The information herein is given in good faith and believed current as of the date of publication and should apply to the current formula version. Because conditions of use are beyond our control, no guarantee, representation or warranty expressed or implied is made. Consult Master Fluid Solutions for further information. For the most recent version of this document, please go to this URL: [https://2trim.us/diw/?plr=CW-8906\\*en\\*eu](https://2trim.us/diw/?plr=CW-8906*en*eu)

WEDOLiT CW 8906

©2019-2024 Master Fluid Solutions™ | 2024-04-29

### Choose WEDOLiT CW 8906:

- Offers high cooling- and flushing properties with a very good wetting behaviour
- Contributes to a high tool life
- Very good application stability
- Almost free of foam
- Offers a very good skin compatibility

### Health and Safety

For further information, see the most recent SDS which is available directly from Master Fluid Solutions.

Hasselsstraße 6-14  
Düsseldorf, 40597  
Germany  
+49 211 41 72 82 00

[info-eu@masterfluids.com](mailto:info-eu@masterfluids.com)

[masterfluids.com/eu/en/](https://masterfluids.com/eu/en/)

