

# WEDOLiT® FS 4700

## Evaporating forming oil

WEDOLiT FS 4700 is a low viscous, solvent-based lubricant for stamping and forming operations of steel, aluminium and non-ferrous metals. The undiluted product is usually applied by spraying, flooding, brushes or by means of rollers.



### Physical Properties Typical Data

Parameter	Typical results	Tested according to
Appearance:	Transparent	Visual
Density at 20°C:	0.79 g/cm <sup>3</sup>	ASTM D 7042
Viscosity at 20°C:	2.2 mm <sup>2</sup> /s	ASTM D 7042
Flash point:	> 65 °C	DIN EN ISO 2719
Copper corrosion:	Not determined*	DIN 51759-1

\*Discolourations of non-ferrous metals should be examined in preliminary tests

### Application Guidelines

Storage must be frost-free between 5 - 40°C.

The minimum durability is 24 months in an original sealed package.

### Additional Information

The information herein is given in good faith and believed current as of the date of publication and should apply to the current formula version. Because conditions of use are beyond our control, no guarantee, representation or warranty expressed or implied is made. Consult Master Fluid Solutions for further information. For the most recent version of this document, please go to this URL: [https://2trim.us/diw/?plr=FS-4700\\*en\\*eu](https://2trim.us/diw/?plr=FS-4700*en*eu)

WEDOLiT® FS 4700

©2026 Master Fluid Solutions™ | 2026-05-08



### Choose WEDOLiT FS 4700:

- Good spreading behaviour, which leads to a uniform wetting of the metal surface
- Stable load carrying capacity and a homogenous sliding behaviour
- Reduces friction and wear and thus contributes to a high tool life
- Leads to clean surfaces and contributes to achieve dimensional accuracy

### Health and Safety

For further information, see the most recent SDS which is available directly from Master Fluid Solutions.

Hasselsstraße 6-14  
Düsseldorf, 40597  
Germany  
+49 211 41 72 82 00

[info-eu@masterfluids.com](mailto:info-eu@masterfluids.com)

[masterfluids.com/eu/en/](https://www.masterfluids.com/eu/en/)

