


WEDOLiT[®] N 22-3

Prelube for deep drawing and stamping



WEDLiT N 22-3 is a thixotropic, non water soluble, deep drawing agent, which was developed for cold forming of coated carbon steels. It is especially applicable for electro galvanised zinc-, zinc nickel coated- and aluminised-sheets. Also good for aluminium and aluminium alloys. The product can be applied by spraying, flooding or rolling.

Fulfils the requirements of all German automotive manufacturers according to VDA-213 and VW-A001, and has been approved by all VDA members.



Physical Properties Typical Data

| Parameter | Typical results | Tested according to |
|---------------------------------------|--------------------------|-------------------------|
| Appearance: | Medium brown, clear | Visual |
| Density at 15°C: | 0.91 g/cm ³ | ASTM D 7042 |
| Viscosity at 40°C: | 120.0 mm ² /s | ASTM D 7042 |
| Flash point: | > 190 °C | DIN EN ISO 2719 |
| Film type: | Oily | Haptical |
| Removability (1.7 g/m ²): | Fulfilled | VW-52.01/VDA 230-201 |
| Draining behaviour (after 24 h) | Fulfilled | VW-PV 52.03/VDA 230-201 |
| Humidity test: | 30 cycles | DIN EN ISO 6270-2 AHT |
| Salt spray performance: | 6 h | DIN EN ISO 9227 NSS |

Application Guidelines

Storage must be frost-free between 5 – 40 °C.
The minimum durability is 12 month in an original sealed package.
It is recommended to homogenize the product before usage.

Additional Information

The information herein is given in good faith and believed current as of the date of publication and should apply to the current formula version. Because conditions of use are beyond our control, no guarantee, representation or warranty expressed or implied is made. Consult Master Fluid Solutions for further information. For the most recent version of this document, please go to this URL: https://2trim.us/diw/?plr=N-22-3*en*eu

WEDOLiT[®] N 22-3
©1999-2025 Master Fluid Solutions™ | 2025-04-10

Choose WEDOLiT N 22-3:

- Applications at ambient temperatures possible
- A preheating of the oil to approximately 40 - 50°C is possible without the loss of the thixotropic effect after cooling
- Acts at the same time as a corrosion protection agent, and therefore a post treatment of the drawn sheets is not necessary
- An agent stable film is formed after drawing
- Can be removed with organic solvents or water soluble, mild alkaline industrial cleaning agents, even after long storage periods
- After grease removal, excellent phosphating is possible

Health and Safety

For further information, see the most recent SDS which is available directly from Master Fluid Solutions.



Hasselsstraße 6-14
Düsseldorf, 40597
Germany
+49 211 41 72 82 00

info-eu@masterfluids.com

masterfluids.com/eu/en/